



HEAD OFFICE :

Plot No. 12, Sector B1, Local Shopping Complex,
Vasant Kunj, New Delhi - 110070
Phone No : +91 11 26139256 - 265
Fax No : +91 11 26125739

WORKS :

28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Taluk : Igatpuri, Dist : Nasik,
Maharashtra, PIN : 422403
Phone : + 91 2553 229100
Fax : + 91 2553 229200

Website : www.jindalpoly.com

**TECHNICAL DATA SHEET
OPP FILMS**

**TRANSPARENT LOW HEAT SEALABLE LOW
COF ONE SIDE CORONA TREATED**

JS15/18/20/25/30/35/40H1-LS

STRUCTURAL CONFIGURATION



- CORONA TREATED HEAT SEAL LOW COF SKIN
- MODIFIED TRANSPARENT INNER SKIN
- TRANSPARENT CORE
- MODIFIED TRANSPARENT INNER SKIN
- UNTREATED LOW HEAT SEAL LOW COF SKIN

APPLICATIONS :

LOW HEAT SEALABLE, ONE SIDE CORONA TREATED, LOW COF FILM FOR SINGLE / TWO PLY PACKAGING STRUCTURE FOR HIGH SPEED PACKAGING APPLICATIONS

DESCRIPTION :

Transparent Low Heat Sealable Low Co-efficient of Friction One Side Corona Treated OPP Film with Excellent Clarity, Slip and Antistatic Properties for Single / Two Ply Laminate for High Speed Packaging Application. The corona treated side is specifically designed for excellent adhesion of inks and lamination adhesive during conversion. Both the sides exhibit very high hot-tack and seal strength.

SALIENT FEATURES :

- Low Seal Initiation Temperature
- Very High Hot-Tack and Seal Strength
- High Surface Gloss and Transparency
- Very Good Barrier Properties
- Excellent Slip and Antistatic Properties
- Excellent Surface Treatment Retention
- Excellent Adhesion of Inks and Adhesive on Treated Side
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability



TECHNICAL DATA SHEET

PROPERTIES	TEST METHOD	UNIT	JS15H1-LS	JS18H1-LS	JS20H1-LS	JS25H1-LS	JS30H1-LS	JS35H1-LS	JS40H1-LS
PHYSICAL									
Thickness	ASTM D 374	Micron	15	18	20	25	30	35	40
Grammage	JPFTM	gm/m ²	13.7	16.4	18.2	22.7	27.3	31.8	36.4
Yield	JPFTM	m ² /kg	73.0	60.9	55.0	44.0	36.6	31.4	27.4
Surface									
Treatment Level	ASTM D2578	dyne/cm	39	39	39	39	39	39	39
Optical									
Haze	ASTM D1003	%	1.8	1.8	1.9	1.9	2.0	2.0	2.2
Gloss at 45° Angle	ASTM D2457	-	88	88	88	88	88	88	88
MECHANICAL									
Coefficient of Friction – Max. (Untreated / Untreated)	ASTM D 1894	Kinetic	0.23	0.23	0.23	0.23	0.23	0.23	0.23
Tensile Strength	ASTM D 882	MD	1250	1250	1250	1250	1250	1250	1250
		TD	2700	2700	2700	2700	2700	2700	2700
Modulus	ASTM D 882	MD	18000	18000	18000	18000	18000	18000	18000
		TD	28000	28000	28000	28000	28000	28000	28000
Elongation	ASTM D 882	MD	210	210	210	210	210	210	210
		TD	70	70	70	70	70	70	70
THERMAL									
Shrinkage at 120 ^o C / 5 min	JPFTM	MD	4.5	4.5	4.0	3.5	3.5	3.5	3.5
		TD	2.5	2.5	2.0	1.5	1.5	1.5	1.5
Seal Initiation Temperature	JPFTM	°C	105	105	105	106	106	107	107
Sealing Strength at 120 ^o C / 2 Bar / 1 Sec	JPFTM	gms/25mm	400	425	450	475	500	525	550
BARRIER									
Water Vapour Transmission Rate	ASTM E 398	gm/ m ² /24h	7.0	6.5	6.0	5.0	4.0	3.0	2.5
Oxygen Gas Transmission Rate	ASTM D 3985	cc/m ² /24h	2000	1850	1800	1700	1600	1500	1450

The values provided in the Technical Data Sheet are typical performance data and are believed to be accurate. These are given in good faith, but users are advised to conduct their own tests on representative samples and not on the actual product dispatched. JINDAL POLY FILMS LIMITED doesn't guarantee or warranty typical values and fitness for its use for a specific purpose. The user is solely responsible for all determinations by the application of this information or the safety and suitability of our products, either alone or in combination with other products.

Storage & Handling:

It is a fact that dyne level decays over time in BOPP films and the decay is further aggravated with extreme environmental conditions. If film rolls are to be stored for a long time, it is preferable to maintain a constant, preferably low temperature (below 30°C) and a low humidity (below 70% RH) to maximize shelf life of the product & to minimize dyne level decay.

JPFTM : JINDAL POLY FILMS TEST METHOD, MD : MACHINE DIRECTION, TD : TRANSVERSE DIRECTION