

HEAD OFFICE:

Plot No. – 12, Sector B1,
Local Shopping Complex, Vasant Kunj,
New Delhi - 110 070 (INDIA).
Tel: 0091-11-26139256 – 265
Fax: 0091-11-26125739
Web site: www.jindalpoly.com

TECHNICAL SPECIFICATION SHEET (J-222M1)

DESCRIPTION: Normal-density Metallised bi-axially oriented polyester film; Metallised on pre-coated co polyester surface and other side corona treated. Metallization on coated surface enhance metal adhesion.

APPLICATIONS: Suitable for flexible packaging application where high barrier and high metal bond is required

SALIENT FEATURES:

- High Metal Bond Strength
- Good Water Vapour and Gas Barrier properties
- Good Lamination Bond Strength
- Excellent Machinability

			TECHNICAL DATA	
PROPERTIES	TEST METHOD	UNIT	J-222M1	
PHYSICAL				
Thickness	ASTM D 374	Micron (Gauge)	12 (48)	
Yield	JPFTM	m ² /kg (in ² /lb)	59.5 (41800)	
OPTICAL				
* Optical Density	By Tobias make Instrument	%	2.2 ± 5%	
BOND STRENGTH				
Metal to PET Bond Strength	JPFTM	g /inch	400	
MECHANICAL				
Tensile Strength (Min)	MD	ASTM D 882	Kg/cm ² (psi)	2000 (28500)
	TD		Kg/cm ² (psi)	1900 (27000)
Elongation (Min)	MD	ASTM D 882	%	90
	TD		%	90
Coefficient of Friction (Metal to film) (Max)	St	ASTM D 1894	–	0.75
	Dy		–	0.70
THERMAL				
Shrinkage (MAX) (150 ⁰ C / 30 min)	MD	ASTM D 1204	%	2.8
	TD		%	0.4
SURFACE				
Wetting tension (Metallised surface)	ASTM D 2578	dyne/cm	54	
Wetting tension (Corona surface) (Min)	ASTM D 2578	dyne/cm	52	
BARRIER				
WVTR (38 ⁰ C & 90% RH) (Max)	ASTM E 1249	g / m ² / day (g / 100 inch ² / day)	1.00 (0.065)	
OTR (23 ⁰ C & 0% RH) (Max)	ASTM D 3985	cc / m ² / day (cc / 100 inch ² / day)	1.20 (0.08)	

*These properties can be changed to meet the specific requirements of the customer.

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

WORKS:

28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Maharashtra
Phone : + 91 2553 229100, 231002 / 3 / 5
Fax: + 91 2553 231004

