

**HEAD OFFICE:**Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,
New Delhi - 110 070 (INDIA).

Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739

Web site: www.jindalpoly.com**TECHNICAL SPECIFICATION SHEET (J-500M0)****DESCRIPTION:** Normal density Metallised on clear bi-axially oriented polyester film; Metallised on plain surface and other side plain.**APPLICATIONS:** Suitable for flexible packaging, glitter powder application, especially for higher gloss**SALIENT FEATURES:**

- Good Metal Bond Strength
- High gloss
- Good Lamination Bond Strength
- Excellent Machinability

TECHNICAL DATA

PROPERTIES		TEST	UNIT	J-500M0	
PHYSICAL					
Thickness		ASTM D 374	Micron (Gauge)	23 (92)	50 (200)
Yield		JPFTM	m ² /kg (in ² /lb)	31 (21800)	14.2 (10000)
OPTICAL					
*Optical Density		By Tobias make Instrument	%	2.2 ± 5%	2.2 ± 5%
BOND STRENGTH					
Metal to PET Bond Strength		JPFTM	g /inch	120	120
MECHANICAL					
Tensile Strength (Min)	MD	ASTM D 882	Kg/cm ² (psi)	1900 (27000)	1800 (25600)
	TD		Kg/cm ² (psi)	1800 (25600)	1800 (25600)
Elongation (Min)	MD	ASTM D 882	%	90	90
	TD		%	85	85
Coefficient of Friction (Metal to film) (Max)	St	ASTM D 1894	–	0.75	0.70
	Dy		–	0.70	0.60
THERMAL					
Shrinkage (150°C / 30 min) (MAX)	MD	ASTM D 1204	%	2.8	2.8
	TD		%	0.4	0.4
SURFACE					
Wetting tension (Pre-Metallized surface)		ASTM D 2578	dyne/cm	44	44
BARRIER					
WVTR (38 °C & 90% RH) (Max)		ASTM E 398	g / m ² / day (g / 100 inch ² / day)	0.8 (0.052)	0.8 (0.052)
OTR (23 °C & 0% RH) (Max)		ASTM D 3985	cc / m ² / day (cc / 100 inch ² / day)	1.00 (0.065)	1.00 (0.065)

*These properties can be changed to meet the specific requirements of the customer.

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

WORKS:28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Maharashtra
Phone : + 91 2553 229100, 231002 / 3 / 5
Fax: + 91 2553 231004

**HEAD OFFICE:**

Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,
New Delhi - 110 070 (INDIA).
Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739
Web site: www.jindalpoly.com

TECHNICAL SPECIFICATION SHEET (J-500M0)

DESCRIPTION: Normal density Metallised on clear bi-axially oriented polyester film; Metallised on plain surface

APPLICATIONS: Suitable for sequence, glitter powder application and other industrial application.

SALIENT FEATURES:

- Good Metal Bond Strength
- High gloss
- Good Lamination Bond Strength
- Excellent Machinability

TECHNICAL DATA

PROPERTIES	TEST METHOD	UNIT	J-500M0			
PHYSICAL						
Thickness	ASTM D 374	Micron (Gauge)	100 (400)	110 (440)	125 (500)	
Yield	JPFTM	m ² /kg (in ² /lb)	7.1(4990)	6.5 (4550)	5.7 (4000)	
OPTICAL						
*Optical Density	By Tobias make Instrument	%	2.2 ± 5%	2.2 ± 5%	2.2 ± 5%	
MECHANICAL						
Tensile Strength (Min)	MD	ASTM D 882	Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
	TD		Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
Elongation (Min)	MD	ASTM D 882	%	120	120	120
	TD		%	100	100	100
Coefficient of Friction (Metal to film) (Max)	St	ASTM D 1894	–	0.65	0.65	0.65
	Dy		–	0.60	0.60	0.60
THERMAL						
Shrinkage (150°C / 30 min) (Max)	MD	ASTM D 1204	%	2.5	2.5	2.5
	TD		%	1.5	1.5	1.5
SURFACE						
Wetting tension (Pre-Metallized surface) (Min)	ASTM D 2578	dyne/cm	44	44	44	

*These properties can be changed to meet the specific requirements of the customer.

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

WORKS:

28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Maharashtra
Phone : + 91 2553 229100, 231002 / 3 / 5
Fax: + 91 2553 231004

**HEAD OFFICE:**

Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,
New Delhi - 110 070 (INDIA).
Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739
Web site: www.jindalpoly.com

TECHNICAL SPECIFICATION SHEET (J-500M0)

DESCRIPTION: Normal density Metallised on clear bi-axially oriented polyester film; Metallised on plain surface

APPLICATIONS: Suitable for sequence, glitter powder application and other industrial application.

SALIENT FEATURES:

- Good Metal Bond Strength
- High gloss
- Good Lamination Bond Strength
- Excellent Machinability

TECHNICAL DATA

PROPERTIES	TEST METHOD	UNIT	J-500M0			
PHYSICAL						
Thickness	ASTM D 374	Micron (Gauge)	135 (540)	140 (560)	150 (600)	
Yield	JPFTM	m ² /kg (in ² /lb)	5.3 (3710)	5.1 (3580)	4.7 (3340)	
OPTICAL						
*Optical Density	By Tobias make Instrument	%	2.2 ± 5%	2.2 ± 5%	2.2 ± 5%	
MECHANICAL						
Tensile Strength (Min)	MD	ASTM D 882	Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
	TD		Kg/cm ² (psi)	1700 (24200)	1700 (24200)	1700 (24200)
Elongation (Min)	MD	ASTM D 882	%	120	120	120
	TD		%	100	100	100
Coefficient of Friction (Metal to film) (Max)	St	ASTM D 1894	–	0.65	0.65	0.65
	Dy		–	0.60	0.60	0.60
THERMAL						
Shrinkage (150°C / 30 min) (Max)	MD	ASTM D 1204	%	2.5	2.5	2.5
	TD		%	1.5	1.5	1.5
SURFACE						
Wetting tension (Pre-Metallized surface)	ASTM D 2578	dyne/cm	44	44	44	

*These properties can be changed to meet the specific requirements of the customer.

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

WORKS:

28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Maharashtra
Phone : + 91 2553 229100, 231002 / 3 / 5
Fax: + 91 2553 231004