

**HEAD OFFICE:**

Plot No. – 12, Sector B1, Local Shopping Complex, Vasant Kunj,  
New Delhi - 110 070 (INDIA).  
Tel: 0091-11-26139256 – 265, Fax: 0091-11-26125739  
Web site: [www.jindalpoly.com](http://www.jindalpoly.com)

**TECHNICAL SPECIFICATION SHEET (J-700M0)**

**DESCRIPTION:** Normal density metallized bi-axially oriented polyester film; Metallized on plain surface and other side plain.

**APPLICATIONS:** Suitable for flexible packaging application,

**SALIENT FEATURES:**

- Isotropic mechanical property
- High thermal stability and good machinability.
- Good Metal Bond Strength
- Good Water Vapour and Gas Barrier properties

**TECHNICAL DATA**

PROPERTIES		TEST METHOD	UNIT	J-700M0	
<b>PHYSICAL</b>					
Thickness		ASTM D 374	Micron (Gauge)	12 (48)	23 (92)
Yield		JPFTM	m <sup>2</sup> /kg (in <sup>2</sup> /lb)	59.5 (41800)	31 (21800)
<b>OPTICAL</b>					
*Optical Density		By Tobias make Instrument	%	2.2 ± 5%	2.2 ± 5%
<b>BOND STRENGTH</b>					
Metal to PET Bond Strength		JPFTM	g /inch	150	150
<b>MECHANICAL</b>					
Tensile strength (Min)	MD	ASTM D 882	Kg/cm <sup>2</sup> (psi)	2000 (28500)	1900 (27000)
	TD		Kg/cm <sup>2</sup> (psi)	1900 (27000)	1800 (25600)
Elongation (Min)	MD	ASTM D 882	%	90	90
	TD		%	90	90
Coefficient of Friction (Metal to film) (Max)	St	ASTM D 1894	–	0.75	0.70
	Dy		–	0.70	0.65
<b>ISOTROPIC</b>					
Ratio OF TS (+45° / -45°)		Internal	–	0.6 – 1.4	0.6 – 1.4
<b>THERMAL</b>					
Shrinkage (MAX) (150°C / 30 min)	MD	ASTM D 1204	%	2.5	2.5
	TD		%	0.4	0.4
<b>BARRIER</b>					
WVTR (38 °C & 90% RH) (Max)		ASTM E 398	g / m <sup>2</sup> / day (g / 100 inch <sup>2</sup> / day)	1.00 (0.065)	0.80 (0.055)
OTR (23 °C & 0% RH) (Max)		ASTM D 3985	cc / m <sup>2</sup> / day (cc / 100 inch <sup>2</sup> / day)	1.20 (0.08)	1.00 (0.065)

\*These properties can be changed to meet the specific requirements of the customer.

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

**WORKS:**

28 - KM, Stone, Nashik - Igatpuri Road,  
Village : Mundegaon, Maharashtra  
Phone : + 91 2553 229100, 231002 / 3 / 5  
Fax: + 91 2553 231004