



HEAD OFFICE :

Plot No. 2, Sector B1, Local Shopping Complex,
Vasant Kunj,
New Delhi - 110070
Phone No : +91 11 26139256 - 265
Fax No : +91 11 26125739

WORKS :

28 - KM, Stone, Nashik - Igatpuri Road,
Village : Mundegaon, Maharashtra
Phone : + 91 2553 229100
Fax : + 91 2553 229200

Website : www.jindalpoly.com

**TECHNICAL DATA SHEET
OPP FILMS**

**ONE SIDE METALLISED OTHER SIDE NON
HEAT SEALABLE CORONA TREATED**

JS15/18/20/25/30/35N2-MD

STRUCTURAL CONFIGURATION



- PLASMA TREATED METALLISED SKIN
- MODIFIED TRANSPARENT INNER SKIN
- TRANSPARENT CORE
- MODIFIED TRANSPARENT INNER SKIN
- CORONA TREATED NON HEAT SEALABLE SKIN

APPLICATIONS :

NON HEAT SEALABLE METALLISED FILM FOR SANDWICH LAYER IN THREE PLY LAMINATE PACKAGING STRUCTURE.

DESCRIPTION :

One Side Metallised, Other Side Corona Treated Non Heat Sealable OPP Film for use as Sandwich Layer in Three Ply Laminated Packaging Structure. The film exhibits excellent water vapour and gas barrier properties. During metalisation process film is treated with plasma for enhancing metal adhesion and barrier properties. Metallised side is specifically designed for excellent surface treatment retention behaviour as well as very good anchorage with lamination adhesives. The corona treated non heat sealable side is also designed for excellent anchoring to lamination adhesive.

SALIENT FEATURES :

- Excellent Surface Gloss on Metallised Side
- Excellent Water Vapour and Gas Barrier Properties
- Excellent Adhesion of Aluminium
- Very Good Anchorage of Lamination Adhesive on Metallised Side as well as Corona Treated Side
- Very Good Metal Bond Strength
- Very Good Lamination Bond Strength
- Excellent Machinability



TECHNICAL DATA SHEET

PROPERTIES	TEST METHOD	UNIT	JS15N2-MD	JS18N2-MD	JS20N2-MD	JS25N2-MD	JS30N2-MD	JS35N2-MD
PHYSICAL								
Thickness	ASTM D 374	Micron	15	18	20	25	30	35
Grammage	JPFTM	gm/m ²	13.7	16.4	18.2	22.75	27.3	31.85
Yield	JPFTM	m ² /kg	73.0	61.0	54.9	44.0	36.6	31.4
SURFACE								
Treatment level – Non Metallised side (Min.)	ASTM D2578	Dyne/cm	38	38	38	38	38	38
OPTICAL								
Optical Density (Min)	JPFTM	-	2.0	2.0	2.0	2.0	2.0	2.0
MECHANICAL								
Coefficient of Friction – Max. (Non Metallised /NonMetallised)	ASTM D 1894	Kinetic	0.48	0.48	0.48	0.48	0.48	0.48
Tensile Strength	ASTM D 882	MD	1275	1275	1275	1275	1275	1275
		TD	2600	2600	2600	2600	2600	2600
Modulus	ASTM D 882	MD	18000	18000	18000	18000	18000	18000
		TD	28000	28000	28000	28000	28000	28000
Elongation	ASTM D 882	MD	190	190	190	190	190	190
		TD	70	70	70	70	70	70
THERMAL								
Shrinkage at 120° C / 5 min	JPFTM	MD	4.0	3.5	3.5	3.5	3.5	3.5
		TD	2.0	1.5	1.5	1.5	1.5	1.5
Seal Initiation Temperature	JPFTM	°C	-	-	-	-	-	-
Sealing Strength at 120° C / 2 Bar / 1 Sec	JPFTM	gms/25mm	-	-	-	-	-	-
BARRIER								
Water Vapour Transmission Rate	ASTM F 1249	gm/ m ² /24h	< 0.80					
Oxygen Gas Transmission Rate	ASTM D 3985	cc/m ² /24h	< 60					

The values provided in the Technical Data Sheet are typical performance data and are believed to be accurate. These are given in good faith, but users are advised to conduct their own tests on representative samples and not on the actual product dispatched. JINDAL POLY FILMS LIMITED doesn't guarantee or warranty typical values and fitness for its use for a specific purpose. The user is solely responsible for all determinations by the application of this information or the safety and suitability of our products, either alone or in combination with other products.

Storage & Handling:

It is a fact that dyne level decays over time in BOPP films and the decay is further aggravated with extreme environmental conditions. If film rolls are to be stored for a long time, it is preferable to maintain a constant, preferably low temperature (below 30°C) and a low humidity (below 70% RH) to maximize shelf life of the product & to minimize dyne level decay.

Use of in-line 'corona treatment booster' or a 'primer' is advisable in metallised films for good adhesion.

JPFTM : JINDAL POLY FILMS TEST METHOD, MD : MACHINE DIRECTION, TD : TRANSVERSE DIRECTION